



- Meets UL 2024
- VW-1, FAR 25 Approved
- Expands Up To 150%
- Resists Gasoline And Engine Chemicals
- Cut And Abrasion Resistant
- Easy To Install



Cut Cleanly
Hot Knife

Material HT

Ethylene-chlorotrifluoroethylene

Grade

HTN

Monofilament Diameter

0,28mm

Drawing Number

TF001HT-WD



Nominal Size	Part #	Expansion Range		Put-Ups		Available Colors	Kgs/100m
		Min	Max	Bulk Spool	Shop Spool		
3,2mm	HTN0.13	2,4mm	6,4mm	304,8m	68,6m	3	0,37
6,4mm	HTN0.25	3,2mm	11,1mm	304,8m	61,0m	3	0,57
9,5mm	HTN0.38	4,8mm	15,9mm	152,4m	38,1m	3	1,28
12,7mm	HTN0.50	6,4mm	19,1mm	152,4m	30,5m	3	1,64
19,1mm	HTN0.75	12,7mm	31,8mm	76,2m	22,9m	3	2,53
25,4mm	HTN1.00	15,9mm	41,3mm	76,2m	19,8m	3	3,27
31,8mm	HTN1.25	19,1mm	44,5mm	76,2m	15,2m	3	3,87
44,5mm	HTN1.75	31,8mm	69,9mm	61,0m	9,1m	3	6,55
50,8mm	HTN2.00	38,1mm	88,9mm	61,0m	15,2m	3	6,85

Very Low Outgassing, Self-Extinguishing UL-2024 Plenum Rated Sleeving

Colors Available:
BK, TW, & TB

HALAR® (HT) self-extinguishing sleeving is used where flammability, high temperature endurance and low outgassing are primary concerns. HT is braided from 11 mil ethylene chlorotrifluoroethylene (ECTFE) copolymer monofilament.

Because of its low flame spread and smoke generation properties, HT has received UL 2024 and NFPA 262 plenum listings, UL flame resistance rating of VW-1 and exceeds automotive industry requirements of FMVSS 302, as well as aviation industry requirements of FAR 25.

HT resists a wide range of corrosive chemicals and organic solvents, including strong acids, chlorine and aqueous caustics. HALAR® ECTFE also maintains useful properties on exposure to Cobalt 60 radiation at doses up to 200 megarads.


Halar's low outgassing, as well as its heat, chemical and radiation properties, make it ideal for use as a component in technologically advanced applications.

Colors Available:



Black (BK),
White with Black Tracer (TW),
Black with White Tracer (TB).

Halar® is a registered trademark of the Solvay Solexis Corporation.



Plenum VW-1



CLEAN FAR-25





ABRASION **FLAMMABILITY**

Abrasion Resistance
Medium

Rating _____ FAR 25, VW-1

Abrasion Test Machine
Taber 5150

Abrasion Test Wheel
Calibrase H-18

Abrasion Test Load
500g

Room Temperature
71°F

Humidity
58%

Material Destroyed
600 Test Cycles

Pre-Test Weight
6,354.9 mg

Post-Test Weight
5,922.8 mg

Test End Loss Of Mass
Point Of Destruction
432.1 mg

CHEMICAL RESISTANCE


1=No Effect 4=More Affected
2=Little Effect 5=Severely Affected
3=Affected

Aromatic Solvents _____	1
Aliphatic Solvents _____	1
Chlorinated Solvents _____	1
Weak Bases _____	1
Salts _____	1
Strong Bases _____	1
Salt Water 0-S-1926 _____	1
Hydraulic Fluid MIL-H-5606 _____	1
Lube Oil MIL-L-7808 _____	1
De-Icing Fluid MIL-A-8243 _____	1
Strong Acids _____	1
Strong Oxidants _____	1
Esters/Ketones _____	2
UV Light _____	1
Petroleum _____	1
Fungus ASTM G-21 _____	1
Halogen Free _____	No
RoHS _____	Yes
SVHC _____	

Melt Point
ASTM D-2117
482°F (250°C)

Maximum Continuous
Mil-I-23053
302°F (150°C)

Minimum Continuous
-103°F (-75°C)



PHYSICAL PROPERTIES

Monofilament Diameter _____	0,28mm
ASTM D-204	
Flammability Rating _____	FAR 25, VW-1
FMVSS-302 Approved	
Recommended Cutting _____	Hot Knife
Colors _____	3
Wall Thickness _____	0,7mm
Tensile Strength (Yarn) _____	4.3
ASTM D-2256 Lbs	
Specific Gravity ASTM D-792 _____	1.68
Moisture Absorption _____	.02
% ASTM D-570	
Hard Vacuum Data _____	
ASTM E-595 at 10-5 torr	
TML _____	.18
CVCM _____	.02
WVR _____	0
Smoke D-Max _____	94
ASTM E-662	
Outgassing _____	Low
Oxygen Index _____	64
ASTM D-2863	