



- Excellent Noise Suppression
- Abrasion Resistant
- Extremely Lightweight
- Attractive Appearance
- Does Not Trap Heat Or Moisture

Put-Ups

Nominal Size	Part #	Expansion Range		Bulk Spool	Shop Spool	Available Colors	Kgs/100m
		Min	Max				
3,2mm	NRN0.13BK	3,2mm	4,8mm	152,4m	30,5m	Black	0,45
6,4mm	NRN0.25BK	6,4mm	9,5mm	152,4m	30,5m	Black	0,75
9,5mm	NRN0.38BK	9,5mm	12,7mm	76,2m	30,5m	Black	1,34
12,7mm	NRN0.50BK	12,7mm	19,1mm	76,2m	30,5m	Black	1,64
15,9mm	NRN0.63BK	15,9mm	25,4mm	76,2m	30,5m	Black	2,23
19,1mm	NRN0.75BK	19,1mm	31,8mm	76,2m	22,9m	Black	2,98
25,4mm	NRN1.00BK	25,4mm	41,3mm	76,2m	15,2m	Black	3,57



**Cut Cleanly
Hot Knife**

Material
Polyethylene Terephthalate

Grade
NRN

Wall Thickness
0,64mm


Self-Fitting Protective Oversleeve

Flexo® Noise Reduction (NR) is a biaxially braided sleeving combining monofilament and multifilament PET yarns to create a full coverage expandable sleeve that substantially reduces noise on wires, tubes and hoses. The lightweight, rugged construction also provides protection from abrasion and vibration that is far superior to foam harness sleeves. NR expands for easy installation over splices and connectors and is flexible enough for tight radius applications.

NR is used in body wiring harnesses, instrument panel and lighting wiring, cable and hose assemblies, and other limited access applications where noise reduction is desirable.

The braided construction will not hold moisture and drains quickly when immersed.

Colors Available:
Black (BK)





ABRASION FLAMMABILITY

Abrasion Resistance
Medium

Abrasion Test Machine
Taber 5150

Abrasion Test Wheel
Calibrase H-18

Abrasion Test Load
500g

Rating _____ *UL94
*UL 94 V-O Raw Material

CHEMICAL RESISTANCE


1=No Effect 4=More Affected
2=Little Effect 5=Severely Affected
3=Affected

Aromatic Solvents _____	2
Aliphatic Solvents _____	1
Chlorinated Solvents _____	3
Weak Bases _____	1
Salts _____	1
Strong Bases _____	2
Salt Water 0-S-1926 _____	1
Hydraulic Fluid MIL-H-5606 _____	1
Lube Oil MIL-L-7808 _____	1
De-Icing Fluid MIL-A-8243 _____	1
Strong Acids _____	3
Strong Oxidants _____	2
Esters/Ketones _____	1
UV Light _____	1
Petroleum _____	1
Fungus ASTM G-21 _____	1
Halogen Free _____	Yes
RoHS _____	Yes
SVHC _____	None

Melt Point
ASTM D-2117
446°F (230°C)

Maximum Continuous
Mil-I-23053
257°F (125°C)

Minimum Continuous
-22°F (-30°C)



PHYSICAL PROPERTIES

Monofilament Diameter _____	0,25mm
ASTM D-204	
Flammability Rating _____	*UL94
*UL 94 V-O Raw Material	
Recommended Cutting _____	Scissor/HK
Colors _____	1
Wall Thickness _____	0,64mm
Tensile Strength (Yarn) _____	7,5
ASTM D-2256 Lbs	
Specific Gravity ASTM D-792 _____	1,38
Moisture Absorption _____	0,1-0,2
% ASTM D-570	
Hard Vacuum Data _____	
ASTM E-595 at 10-5 torr	
TML _____	0,19
CVCM _____	0,00
WVR _____	0,16
Outgassing _____	Med
Oxygen Index _____	21
ASTM D-2863	