

- High Chemical Resistance
- Low Outgassing
- Halogen Free
- Very Light Weight
- V-O Flammability Rating
- Wear Resistant
- High Strength Alternative to Fluoropolymers



Material Polyetheretherketone

Grade PKN

Monofilament Diameter 0,25mm

Drawing Number TF001PK-WD



7 boulevard de l'Odet 35740 Pacé - France + 33 2 23 30 05 15 www.CableOrganizer.fr

				- Tut	ohs –		
Nominal	Part	Expansion Range		Bulk	Shop	Available	Kgs/
Size	#	Min	Max	Spool	Spool	Colors	100m
3,2mm	PKN0.13BK	1,6mm	7,9mm	304,8m	68,6m	Black (BK)	0,24
6,4mm	PKN0.25BK	2,8mm	14,3mm	304,8m	61,0m	Black (BK)	0,28
9,5mm	PKN0.38BK	4,0mm	15,9mm	152,4m	38,1m	Black (BK)	0,46
12,7mm	PKN0.50BK	4,8mm	23,8mm	152,4m	30,5m	Black (BK)	0,65
15,9mm	PKN0.63BK	6,4mm	31,8mm	152,4m	30,5m	Black (BK)	0,76
19,1mm	PKN0.75BK	9,5mm	34,9mm	76,2m	22,9m	Black (BK)	0,95

Dut-Ilnc


Call for more size availability

Secures Performance Of Sensitive **Items in Challenging Environments**

Similar to PPS, but with a substantially expanded operating temperature range, PEEK (PolyEtherEther-Ketone) is a high performance advanced polymer with outstanding physical properties. PEEK is inherently flame retardant, with a V-0 flammability rating, will withstand continuous use in superheated water or steam up to 260°C, and resists most acids, solvents and bases. PEEK is FDA approved as a food contact product, resists damage from radiation and will continue to perform in UHV (Ultra High Vacuum) environments. PEEK is extensively used in the aerospace, automotive, teletronic and chemical process industries, and is considered an advanced biomaterial used in medical implants and other biomedical applications. PEEK will withstand thousands of sterilization cycles without damage or degradation. Flexo PEEK expandable sleeving is tightly braided from 10 mil filaments of pure, unfilled PEEK polymer. The sleeving expands to fit over connectors and splices, and provides a full

coverage over wires hoses and cable bundles

in advanced engineering applications.





PEEK[°] is a registered trademark of the Victrex Corporation.





ADVANCED ENGINEERING **Technical Data Sheet**



Rating _____ V-O

CHEMICAL RESISTANCE

1=No Effect 2=Little Effect 3=Affected

4=More Affected 5=Severely Affected

Aromatic Solvents	1
Aliphatic Solvents	1
Chlorinated Solvents	
Weak Bases	1
Salts	
Strong Bases	3
Salt Water 0-S-1926	1
Hydraulic Fluid <i>MIL-H-5606</i>	1
Lube Oil	1
De-Icing Fluid MIL-A-8243	1
Strong Acids	3
Strong Oxidants	1
Esters/Ketones	1
UV Light	1
Petroleum	1
Fungus ASTM G-21	1
Halogen Free	Yes
RoHS	Yes

633°F (334°C)-CODA 500° Maximum Continuous-Mil-I-23053 400° . 500°F (260°C) 300° -

Melt Point

ASTM D-2117

Minimum Continuous -94°F (-70°C)_

700° -

200° -100°

09

-100°_

-200°_

OPERATING TEMPERATURES

PHYSICAL PROPERTIES 0,

Monofilament Diameter	0,25mm	
Recommended Cutting	Hot Knife	
Colors	1	
Wall Thickness	0,64mm	
Abrasion Resistance	Med	
Tensile Strength ASTM D638 (PSI)	13,300	
Specific Gravity ASTM D-792 _	1.3	
Water Absorption %	<0,05	
Elongation ASTM D638 (%)	50	
Electrical: Dielectric Strength <i>ASTM D149 (V/Mil)</i>	>500	
Volume Resistivity ASTM D257 (ohm-cm)	>4,9x10 ¹⁶	
Outgassing	Low	