


- Economical And Easy To Install
- Dual-Colored Monofilament
- Even more color possibilities

Put-Ups

Nominal Size	Part #	Expansion Range		Bulk Spool	Shop Spool	Available Colors	Kgs/ 100m
		Min	Max				
6,4mm	PTD0.25	3,2mm	11,1mm	304,8m	61,0m	2	0,45
9,5mm	PTD0.38	4,8mm	12,7mm	152,4m	38,1m	2	0,85
12,7mm	PTD0.50	6,4mm	19,1mm	152,4m	30,5m	2	1,15
15,9mm	PTD0.63	9,5mm	25,4mm	152,4m	30,5m	2	1,41
19,1mm	PTD0.75	12,7mm	31,8mm	76,2m	22,9m	2	1,79
25,4mm	PTD1.00	15,9mm	41,3mm	76,2m	19,8m	2	1,99
31,8mm	PTD1.25	19,1mm	44,5mm	76,2m	15,2m	2	2,38
38,1mm	PTD1.50	25,4mm	54,0mm	61,0m	12,2m	2	2,92
44,5mm	PTD1.75	31,8mm	69,9mm	61,0m	9,1m	2	3,65



Cut Cleanly  
Hot Knife

**Material**  
Polyethylene Terephthalate

**Grade**  
PTD


**Monofilament Diameter**  
0,25mm

### Flexo PrisMix - Braided Camo

Prismix (PTD) utilizes a cutting-edge dual-colored monofilament to produce never before possible color combinations.


This new technology creates an incredible random camouflage in our exclusive new Mix series of product. Be sure to utilize Prismix on your next adventure for the best braided camo you have ever seen, or not seen!

Colors Available:



Expedition Mix (EM) and Trail Mix (TM)

Colors Available:  
2 = EM & TM





## ABRASION FLAMMABILITY

**Abrasion Resistance**  
**High**

Rating \_\_\_\_\_ UL94

**Abrasion Test Machine**  
**Taber 5150**

## CHEMICAL RESISTANCE


1=No Effect      4=More Affected  
2=Little Effect    5=Severely Affected  
3=Affected

Aromatic Solvents _____	2
Aliphatic Solvents _____	1
Chlorinated Solvents _____	3
Weak Bases _____	1
Salts _____	1
Strong Bases _____	2
Salt Water 0-S-1926 _____	1
Hydraulic Fluid MIL-H-5606 _____	1
Lube Oil MIL-L-7808 _____	1
De-Icing Fluid MIL-A-8243 _____	1
Strong Acids _____	3
Strong Oxidants _____	2
Esters/Ketones _____	1
UV Light _____	1
Petroleum _____	1
Fungus ASTM G-21 _____	1
Halogen Free _____	Yes
RoHS _____	Yes
SVHC _____	None

Melt Point  
ASTM D-2117  
482°F (250°C)

Maximum Continuous  
Mil-I-23053  
257°F (125°C)

Minimum Continuous  
-94°F (-70°C)



## PHYSICAL PROPERTIES

Monofilament Diameter _____	0,25mm
ASTM D-204	
Flammability Rating _____	UL94
FMVSS-302 Approved	
Recommended Cutting _____	Hot Knife
Colors _____	2
Wall Thickness _____	0,64mm
Tensile Strength (Yarn) _____	7,5
ASTM D-2256 Lbs	
Specific Gravity ASTM D-792 _____	1,38
Moisture Absorption _____	0,1 - 0,2
% ASTM D-570	
Hard Vacuum Data _____	
ASTM E-595 at 10-5 torr	
TML _____	0,19
CVCM _____	0,00
WVR _____	0,16
Smoke D-Max _____	56
ASTM E-662	
Outgassing _____	Medium
Oxygen Index _____	21
ASTM D-2863	